



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : <b>F04B 43/00</b>	<b>A1</b>	(11) International Publication Number: <b>WO 95/06205</b>
		(43) International Publication Date: 2 March 1995 (02.03.95)

(21) International Application Number: PCT/US93/09519


(22) International Filing Date: 1 October 1993 (01.10.93)

(30) Priority Data:  
08/110,684 23 August 1993 (23.08.93) US(71) Applicant: W.L. GORE & ASSOCIATES, INC. [US/US]; 551  
Paper Mill Road, P.O. Box 9206, Newark, DE 19714 (US).(72) Inventors: DELANEY, William, E.; 4 McCormick Drive,  
Hockessin, DE 19707 (US). MINOR, Raymond; 233  
Greenhaven Drive, Elkton, MD 21921 (US). MCGREGOR,  
Gordon, L.; 5 Copper Beech Court, Landenberg, PA 19350  
(US).(74) Agents: JOHNS, David, J. et al.; W.L. Gore & Associates, Inc.,  
551 Paper Mill Road, P.O. Box 9206, Newark, DE 19714  
(US).(81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CZ,  
DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, MG,  
MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK,  
UA, VN, European patent (AT, BE, CH, DE, DK, ES, FR,  
GB, GR, IE, IT, LU, MC, NL, PT, SE).**Published***With international search report.*

(54) Title: PRE-FAILURE WARNING PUMP DIAPHRAGM

## (57) Abstract

This invention provides a conductive strand embedded in a diaphragm in which the strand undergoes changes in electrical properties upon being subjected to stress. A change in electrical conductivity is recorded by an electrical monitoring device connected electrically with the conductive strand. By observing changes in the conductivity that deviate from a predetermined norm, the fatigue or wear on the diaphragm can be detected.



***FOR THE PURPOSES OF INFORMATION ONLY***

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgystan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

-1-

**TITLE OF THE INVENTION**

PRE-FAILURE WARNING PUMP DIAPHRAGM

**FIELD OF THE INVENTION**

5 This invention relates to a failure sensing mechanism for use in flexible chemical barriers. It is particularly suited for detection of impending failure before leaks occur in diaphragms, such as are used in pumps.

**BACKGROUND OF THE INVENTION**

10 Barrier layers of chemically resistant materials such as polytetrafluoroethylene (PTFE) are widely used in industry to protect sensitive parts of machinery or equipment from the corrosive effects of acids or other chemicals. One such use is in pump diaphragms commonly used with air or electrically driven diaphragm pumps. In this application an outer chemically resistant  
15 overlay diaphragm is commonly used to protect an inner rubber diaphragm from materials that would cause rapid failure of the rubber part alone. In other instances the resistant material provides the sole material of construction of the diaphragm.

In all cases the repetitive flexing of the diaphragm  
20 eventually causes failure of the diaphragm. When PTFE is one layer, the PTFE fatigues more readily than commonly used rubbers such as Neoprene, and in those instances, the PTFE fails first. Failure of the diaphragm can result in corrosive material entering a part of the pump that is not designed to come in contact with it.  
25 In many cases the corrosive material can result in damage to the pump. In the case of air driven pumps the corrosive material will often mix with the air stream and will as a result enter the environment and potentially result in damage or in injury. Expensive containment systems sometimes are employed as a result.  
30 Attempts have been made to detect leakage when it occurs or contain it after the fact. Leak detection chambers may be built

-2-

into the pump itself incorporating conductivity sensors, but this results in a more expensive pump design and the need for additional diaphragms to separate the additional detection chambers.

5 In U.S. Patent 4,569,634 to Myron Mantell a metal or graphite detector is embedded inside the body of a diaphragm. When the diaphragm cracks, the graphite is exposed to the fluid being pumped. The fluid is a conductive fluid and the change in the resulting current flow is detected. The method of 4,569,634  
10 however requires a mesh, screen or web of conductive fibers which may result in difficulty in manufacture of diaphragms having long flexing lifetimes. Furthermore this patent requires that the medium being pumped be conductive and thus the usefulness of the invention is limited.

15 U.S. Patent 4,781,535 to Frawley and Mearns describes another method in which a continuous circuit trace is supported within the diaphragm. When the diaphragm fails the trace is broken setting off an alarm. However the patent places no emphasis on the trace composition and describes it only as metallic or steel. With PTFE diaphragms the metal will tend to fail at a different time than the  
20 diaphragm and may not provide sufficient warning.

#### SUMMARY OF THE INVENTION

Unlike the mechanisms described above, this invention provides a conductive strand embedded in a diaphragm in which the strand undergoes changes in electrical properties upon being subjected to  
25 stress. A change in electrical conductivity is recorded by an electrical monitoring device connected electrically with the conductive strand. By observing changes in the conductivity that deviate from a predetermined norm, the fatigue or wear on the diaphragm can be detected.

30 In a preferred form a thin flexible conductive fiber made of conductive PTFE is embedded within a chemical barrier sheet or form made of PTFE. The PTFE sheet, which has good flexing properties and is an excellent barrier layer for chemicals, can then be used to form, either by itself or bonded to rubber, a fully functional  
35 diaphragm. If the conductive fiber is laid out to cover

-3-

substantially the entire area of the diaphragm in a spiral or double spiral or a zigzag or other traversing pattern, it can be passed out of the diaphragm and connected to an electrical sensing circuit. Once the diaphragm incurs fatigue or cracks such as surface stress cracks, the fiber will detect the change in conductivity by suitable electronic means. In one embodiment, the conductive fiber is made of material like that of the diaphragm itself, both being made of PTFE, and the flex life of the diaphragm usually will be about the same as that of the fiber.

10

### DESCRIPTION OF THE DRAWINGS

Figure 1 depicts a three-dimensional view of a typical diaphragm showing electrical leads protruding therefrom.

Figure 2 is a view looking at the diaphragm from the top, and shows one configuration of electrical wiring within the diaphragm (denoted by the dashed lines).

Figure 3 is another view from the top and shows a different configuration of electrical wiring.

Figure 4 is still another top view showing a still different wiring configuration.

Figure 5 shows a cross section of a portion of a pump diaphragm of Figure 1 taken along 5-5.

Figure 6 is a graph depicting percentage in resistance versus linear tension of two conductive wires useful in the invention.

### DESCRIPTION OF THE INVENTION

As used herein, the term "diaphragm" means a flexible element that divides two fluid containing compartments. In a preferred embodiment, PTFE or a laminate in which one layer is PTFE has a conductive PTFE fiber embedded in the PTFE layer. The PTFE fiber can be rendered conductive by filling it with a conductive filler such as metal, metal oxide or conductive carbon, or by plating the fiber. Figure 1 represents a typical diaphragm 10 having a hole 13 for attachment to a pump. The diaphragm is a two-layer composite of PTFE layer 11 and flexible elastomeric layer 12. Leads 14

-4-

protrude from the PTFE layer 11. Leads 14 can be attached to appropriate electronic monitoring means to record a break in the electric circuitry.

5 The fiber is preferably placed closer to the back than to the face of the PTFE layer so that it will be affected by wear late in the useful life of the diaphragm. In one mode the fiber is placed 25 mils deep within a 35 mil (0.89 cm) PTFE diaphragm. This allows a margin of safety (10 mils, 0.025 cm) for detection of stress cracks so that the diaphragm can be replaced prior to any leakage.

10 The fiber is patterned so as to cover most of the surface two dimensionally so that any penetration or crack in the diaphragm will necessarily result in damage to the fiber. One useful pattern is a spiral of pairs of fiber shorted together in the center as depicted in Figure 3. This pattern is useful since the most  
15 commonly seen failure in such a diaphragm is one or more cracks formed in from the face of the diaphragm and proceeding inwards toward the rubber backing in a radial fashion in the flexing portion of the diaphragm. A spiral pattern in the conductive fiber thus will intersect with any radial crack. Alternate patterns  
20 include traversing rows such as is shown in Figure 4, but other geometry's are also possible, such as is shown in Figure 2. In any case the fiber also passes through the edge of the diaphragm 14 to allow connection to electronic circuitry and a source of low voltage power. Window comparator circuitry is well known and  
25 particularly useful in detecting any change in the conductivity of a conductive trace whether up or down.

While the invention is applicable to any flexible diaphragm, it is particularly applicable to diaphragms which are composites of a face layer of polytetrafluoroethylene (PTFE) and an air pressure  
30 side layer of a resilient elastomeric material.

The PTFE layer is preferably a layer of dense PTFE, either full density PTFE or densified stretched PTFE. An example of full density PTFE is skived PTFE. Densified PTFE can be made by compressing porous PTFE. The PTFE material provides the composite  
35 diaphragm with an inert outside surface thereby increasing the durability, and chemical resistance of the diaphragm. The solid PTFE layers other surface is adhered to the resilient elastomeric material. Optionally, this inside other surface may be treated,



-5-

e.g., with alkali naphthanates, to increase the surface energy of the PTFE and thereby increase its adherence to the reinforced flexible composite material.

5 The flexible elastomeric layer can be a thermosetting elastomer, thermoplastic elastomer, or a thermoplastic polymer having a flexural elastic modular (ASTM D790-84A) of less than 1,400 MPa.

10 The thermosetting elastomer can be a fluoroelastomer including perfluoroelastomers, fluoroelastomer containing silicone moieties, nitrile elastomer, acrylic elastomer, olefin diene elastomer, chlorosulfonated polyethylene elastomer, polychloroprene elastomer, butyl and halogenated butyl elastomer, styrene-butadiene elastomer, polydiene elastomer or silicone elastomer, or the like.

15 The thermoplastic elastomer can be a copolyetherester elastomer, polyurethane elastomer, styrene polyolefin block copolymer elastomer, polyamide elastomer, or ethylene copolymer elastomer, or the like.

20 The thermoplastic having a flexural elastic modulus (ASTM-D790-84A) less than 1,400 MPa, can be selected from fluorinated thermoplastics such as copolymers of tetrafluoroethylene, copolymers of vinylidene fluoride, copolymers of chlorotrifluoroethylene, polyolefins, or plasticized polyvinyl chlorides, or the like.

25 The PTFE layer is adhered to the resilient elastomeric layer through any known means, for example, by application of a sufficient amount of heat and pressure. The diaphragm may contain ribs made by placing the PTFE/elastomeric composite into a mold of desired shape and applying heat and pressure.

30 The conductive filler containing fiber is preferably filled with carbon and is preferably a fiber made of expanded porous polytetrafluoroethylene. If desired, the PTFE can be expanded porous PTFE which is comprised of a structure of nodes interconnected by fibrils, as taught in U.S. patents 3,953,566, 4,187,390, and 3,962,153.

35 The fiber can be obtained in a number of ways, e.g., by first making a film of the PTFE. The film may be formed by blending a fine powder PTFE resin with mineral spirit and then adding a conductive particulate filler to obtain a compound of fine powder

PTFE resin and conductive particulate filler, as is described in copending United States application Serial No. 915,484. An aqueous dispersion PTFE resin can be mixed with conductive particulate filler and the mixture is co-coagulated by rapid shearing of the aqueous dispersion, or through destabilization of the aqueous dispersion with salt, acid, polyethylene imine or the like. A coagulum of fine powder PTFE resin and conductive particulate is then formed and dried into cakes. Once dry, the cakes are crumbled and lubricated with a mineral spirit and blended to form a compound.

Either of the above described compounds can then be compressed into a billet and subsequently extruded through a die by a ram-type extruder forming a coherent extrudate. The coherent extrudate is then compressed between a pair of calendar rollers to reduce its thickness. Mineral spirit is removed from the calendered extrudate by passing the extrudate over a series of heated rollers set above the boiling point of the mineral spirits.

The dry extrudate can then be expanded by the general procedure taught in United States Patent 3,953,566 to Gore. The dry coherent calendered extrudate can be initially rapidly stretched uniaxially in a longitudinal direction 1.2x to 5000x its starting length, and preferably 2x to 100x, at a stretch rate over 10% per second at a temperature of between 35 to 327°C. This process produces an expanded porous PTFE matrix in continuous film form in which conductive particulate filler is distributed.

The film may next be slit to a desired width to form a continuous slit film fiber having a substantially rectangular profile. The continuous slit film fiber may then be stretched in a longitudinal direction up to fifty times its length, again through the general method of stretching taught by United States Patent 3,543,566 to Gore. This second stretching step increases the strength of the resultant fiber through increased orientation of the ePTFE matrix. The total amount of stretch is a function of the degree to which the PTFE matrix has been filled with filler--the greater the percentage of particulate filler, the less the continuous slit film fiber may be stretched.

The continuous slit film fiber may subsequently be subjected to a temperature in excess of 342°C in order to perform an



-7-

amorphous locking step. This basic procedure is again taught in United States Patent 3,543,566 to Gore. If the fiber is fully restrained longitudinally, the amorphous locking step further increases the strength and density of the expanded continuous slit  
5 film fiber.

Alternatively, prior to slitting, the ePTFE matrix in continuous film form may be compressed and densified, such as through use of adjacent nip rollers, as is taught in United States Patent 4,985,296 to Mortimer, Jr. Compression and densification  
10 increases contact between individual conductive particulate filler particles thereby increasing conductivity of the ePTFE matrix in continuous film form. To increase the strength of the thin ePTFE matrix in continuous film form, multiple layers of the coherent extrudate can be stacked longitudinally and calendered upon one  
15 another forming a layered article. The layered article is subsequently dried, expanded and densified to produce a thin ePTFE matrix of greater strength when compared to an analogous thin ePTFE matrix produced from a single layer of ePTFE matrix. The thin ePTFE matrix may then be subjected to the amorphous locking step  
20 previously described. The thin ePTFE matrix in continuous film form may then be slit to a desired width by a slitter or similar means for cutting films to form a thin continuous fiber having a substantially rectangular profile.

Once such a fiber is formed, its conductivity can be increased  
25 through densification. Preferably, densification is accomplished by twisting the fiber about its central longitudinal axis. The resultant twisted fiber is more dense than a similar untwisted fiber and appears rounder. Moreover, the twisted fiber exhibits greater maintenance of its volume resistivity upon exposure to  
30 tensile forces when compared to an analogous compressed untwisted fiber. The twisting may comprise 1 to 18 twists per centimeter, with 4 to 11 twists per centimeter being preferred. The relative advantages of employing a twisted conductive fiber over other conductive elements is shown in the graph of Figure 6. Figure 6  
35 depicts the percentage (%) change in resistance versus linear tension (kg) of two different samples of conductors: line 26 is the plot for a conventional flat, filled ePTFE conductive fiber (i.e. showing an increase in resistance with an increase in

tension); and line 30 is the plot of a twisted ePTFE fiber (i.e. showing a decrease in resistance with an increase in tension). Twisting can be achieved on a standard fiber twisting machine.

Fibers can be formed through this procedure having a wide  
5 range of bulk tensile strength and volume resistivities, such as:  
a tensile strength of 65,000 KPa or greater with a volume  
resistivity of  $1 \times 10^3$  ohm cm or less; a tensile strength of 65,000  
KPa or greater with a volume resistivity of 10 ohm cm or less; and  
a tensile strength of 200,000 KPa or greater and a volume  
10 resistivity of  $1 \times 10^3$  or less. Tensile strength may be determined  
using the method described in ASTM Standard D882-81 (i.e.  
calculated by dividing the maximum longitudinal load by the  
original cross-sectional area of the specimen). The test performed  
varied from the test as published with respect to the material  
15 tested. ASTM D882-81 is for testing thin plastic sheeting and not  
fibers. The difference is due to the dimensions of the sample.  
The thickness of the fibers is determined through a snap gauge.  
Care is taken not to crush the sample with the presser foot of the  
snap gauge to obtain an accurate thickness. Width of the sample is  
20 determined through measurement on an optical microscope. The  
samples are tested on a constant rate of grip separation machine to  
break. Force at maximum load samples is determined. The volume  
resistivity of the fibers may be determined using the method  
described in ASTM D257-90, "Standard Test Methods for D-C  
25 Resistance or Conductance of Insulating Material."

To embed the fiber in the PTFE layer of the diaphragm, the  
fiber is placed in a desired pattern trace on the surface of a  
sheet of PTFE. Then another sheet of PTFE is placed on top. This  
assembly is then placed in a bag or other flexible container and a  
30 vacuum drawn. The container is then heated and external pressure  
applied to bind the two PTFE sheets together with the fiber  
enclosed inside (the densified stretched PTFE can be made in the  
same way).

The formed product can then be shaped into a diaphragm or it  
35 can be laminated to an elastomeric sheet, such as neoprene rubber.

In operation an electrical current is applied to one of the  
leads 14 and current flows through the fiber. The current is  
monitored and if a break occurs, the current flow stops and is

detected by an appropriate instrument. In addition, the current can be monitored for electrical change due to pressure on the diaphragm from the liquids being pumped. This is due to the change in conductivity or impedance as the pressure causes the fiber to  
5 change physical dimensions temporarily.

Periodic or constant monitoring of the status of the diaphragm is possible. For instance, a base-line electrical signal can be determined by applying an electric current through the diaphragm when it is first installed. By acquiring a second signal reading  
10 at a later time, the second signal can be compared with the base-line signal to determine if any changes have occurred. Determination and quantification of changes can then be used to chart the operational characteristics of the diaphragm. Further, by establishing a pattern of performance, it may also be possible  
15 to predict when the diaphragm is nearing the end of its operational life.

Using these principles, a number of monitoring techniques may be feasible. It is possible to establish a network of monitors which can provide instant feedback on the condition of a number of  
20 parallel pumps and by providing appropriate conduits and computer controlled valving, diaphragm failure in a first line can be detected and flow can be automatically routed around the defective diaphragm to a parallel second line without shutting down any equipment. A signal can then notify an operator that replacement  
25 of the defective diaphragm is required.

Similarly, with a compressive and/or tension force responsive conductive fiber, a base-line signal can be determined prior to the installation of the diaphragm. Once installed, changes in the electrical properties of the diaphragm can be used to judge the  
30 amount of pressure being applied in operation. In this manner, the amount of pressure on the diaphragm can be readily quantified.

The electrical monitoring apparatus may take any suitable form which will provide some quantitative measurement of an electrical property of the conductive fiber. In its preferred form, the  
35 electrical apparatus comprises an analog or digital meter or signal generating device which simply provides a measure of conductivity or impedance or the like.

-10-

Preparation of Fiber

A conductive fiber was produced in the following manner.

5 A mixture of 85% by weight of a fine powder PTFE resin in an aqueous dispersion and 15% by weight of a conductive carbon black (Ketjenblack 300-J available from Akzo Chemical) was made. First a slurry was made of carbon black in deionized water, and agitated with a rotating impeller. Fine powder PTFE aqueous dispersion (AD-059, available from ICI Americas Inc.) was added, and the carbon black and PTFE co-coagulated. After drying, the coagulum was  
10 combined in a blender with an amount of an odorless mineral spirit forming a compound, the compound was compressed into a billet, and the billet extruded to form a coherent extrudate.

The coherent extrudate was compressed between calender rolls and the odorless mineral spirit was volatilized. The dry coherent  
15 calendered extrudate was subsequently expanded at a ratio of 2:1 at a temperature of 270°C.

The dry coherent calendered extrudate was slit to 7.6mm widths by passing the dry coherent calendered extrudate between a set of gapped blades. The slit coherent extrudate was then expanded  
20 uniaxially in the longitudinal direction at a ratio of 19.2 to 1 and subsequently subjected to an amorphous locking step by exposing it to temperatures over 340°C.

Example

A continuous spiral of carbon filled (15% by weight) ePTFE  
25 thread (denier 684) obtained from W. L. Gore & Associates, Inc. was patterned by hand onto a sheet of full density PTFE approximately two feet by three feet and 10 mils thick an additional 10 mils of PTFE were laid on top. The lead portions of the spiral were protected from contact with the PTFE by means of a strip of  
30 polyimide film on each side. The assembly was placed between two steel plates and enclosed in a bag made of polyimide film. A means was provided to draw a vacuum inside the bag and the assembly was inserted into an autoclave. A vacuum of 29 inches of mercury was drawn on the bag while a pressure of 250 psi was applied within the

-11-

autoclave chamber. The temperature was raised to approximately 370°C. In this way the PTFE was sintered together into one 20 mil sheet with the carbon filled fiber embedded in the center.

5 The sheet described above was etched by immersing for 30 seconds in an alkali naphthanate solution available commercially under the trademark TETRA-ETCH from W. L. Gore & Associates, Inc., Elkton, Maryland. A ten inch diameter circular piece containing the carbon filled spiral was cut from the resulting sheet and a 30% toluene solution of a bonding agent (Chemlok 250 available from the  
10 Lord Corporation of Erie, Pennsylvania) was applied by brush and allowed to dry.

A 4.2mm thick layer of an elastomeric polymer cut to the same dimensions was applied to the adhesive previously applied to the PTFE surface (Neoprene compound based on Neoprene GK available from  
15 E. I. duPont de Nemours & Co. of Wilmington, Delaware). The elastomeric material polymer was adhered to the PTFE surface by placing them into a platen press heated to 93°C for about 30 seconds.

The resulting pre-form was placed in a diaphragm mold. The  
20 mold was placed in a platen press which applied 7580 MPa to the composite at a temperature of 170°C for 20 minutes. The mold was cooled while still under pressure until it reached 70°C,

The resulting diaphragm was removed from the mold and any extra material was trimmed from the final part. This part was then  
25 installed in a Wilden M-4 pump driven by 400 N of air pressure against a 127 cm head of water at a rate of 66 cycles per minute. The leads were connected to a hand held resistance meter. The resistance was measured at .03 megohms. The diaphragm was run until the resistance suddenly climbed to 20 megohms at which point  
30 the test was stopped and the pump disassembled to inspect the diaphragm. Upon inspection it was found that the diaphragm had developed several severe radial creases resulting in a partial severance of the conductive fiber. The pump had been run 289,000 cycles.



**CLAIMS:**

1. A flexible diaphragm comprising:  
a diaphragm body;  
a conductive element embedded over substantially the entire  
5 area of said body;  
the conductive element transmitting a change in conductivity  
in response to a change on pressure stress placed on said  
body;  
the ends of said conductive element being exposed for  
10 connection to an electrical system.
2. A flexible diaphragm containing one or more layers of flexible  
material in which at least one layer is comprised of  
polytetrafluoroethylene, said polytetrafluoroethylene layer  
having embedded within it an electrically conductive  
15 polytetrafluoroethylene fiber trace, in which the ends of the  
fiber trace are exposed for connection to an electrical  
system.
3. The diaphragm of Claim 2 in which the fiber trace is patterned  
so as to cover substantially all the area within the periphery  
20 of the pump.
4. The diaphragm of Claim 3 wherein the trace pattern is in the  
form of a spiral.
5. The diaphragm of Claim 4 wherein the diaphragm is circular and  
the trace pattern is in the form of a radially disposed trace  
25 covering substantially the entire area of the diaphragm.
6. The diaphragm of Claim 2 where the polytetrafluoroethylene of  
said layer is densified polytetrafluoroethylene, and the  
polytetrafluoroethylene in said fiber is expanded porous  
polytetrafluoroethylene.
- 30 7. The diaphragm of Claim 6 wherein the electrical conductivity  
in the fiber is provided by particles of conductive carbon.
8. The diaphragm of Claim 1 or 2 wherein the diaphragm is  
designed for use in a diaphragm pump.
9. The diaphragm of Claim 2 wherein the polytetrafluoroethylene  
35 fiber trace has been twisted.
10. A method for verifying the condition of a pump diaphragm which  
comprises:




-13-


- providing a diaphragm which comprises a body, a conductive fiber element within the body, and means to connect the conductive element to monitoring apparatus;  
causing the conductive fiber element to transmit different  
5 signals when stresses are applied to the diaphragm;  
mounting the diaphragm in a pump;  
monitoring the condition of the diaphragm by measuring changes in conductivity through the conductive element.
11. A method for constructing a pump diaphragm which comprises:  
10 providing a diaphragm body;  
embedding within the body an electrically conductive element comprising a polymer filled with electrically conductive particles, the conductive element adapted to undergo changes in electrical property when structural change occurs in the  
15 body;  
including at least one electrical lead providing an electrical connection between the conductive element and a monitoring apparatus.

1/2


**FIG. 1**




**FIG. 2**



**FIG. 3**



**FIG. 4**



**FIG. 5**





FIG. 6



## INTERNATIONAL SEARCH REPORT

Intern: 1 Application No

PCT/US 93/09519

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 F04B43/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 F04B G01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X Y A	FR,A,2 196 514 (MATSUSHITA) 15 March 1974 see page 2, line 25 - page 3, line 21 see page 6, line 22 - line 25; figures 4,5 ---	1 2,3 6,7
X Y	GB,A,2 258 732 (SHIMIZU) 17 February 1993 see page 10, line 6 - line 15; figures 2,11 see page 14, line 14 - page 16, line 2 see page 20, line 15 - page 21, line 24 ---	1 2,3
A	WO,A,91 17701 (MEDEX) 28 November 1991 see page 7, last paragraph - page 8, paragraph 3; figures 4-8 --- -/--	1,2

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance  
"E" earlier document but published on or after the international filing date  
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)  
"O" document referring to an oral disclosure, use, exhibition or other means  
"P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention  
"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone  
"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.  
"&" document member of the same patent family

Date of the actual completion of the international search

23 March 1994

Date of mailing of the international search report

11. 04. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

Bertrand, G

# INTERNATIONAL SEARCH REPORT

Intern: 1 Application No

PCT/US 93/09519

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A,4 569 634 (MANTELL) 11 February 1986 cited in the application see column 1, line 16 - line 21 see column 3, line 29 - column 4, line 61; figures 4-6 ---	1-4,8, 10,11
A	EP,A,0 321 225 (MEDEX) 21 June 1989  see column 2, line 13 - line 40; figures 1,2 ---	1-3,10, 11
A	US,A,4 781 535 (FRAWLEY) 1 November 1988 cited in the application see column 6, line 15 - line 40; figures 1,2,6 -----	1,2,5, 10,11

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 93/09519

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR-A-2196514	15-03-74	NONE	
GB-A-2258732	17-02-93	JP-A- 5332965	17-12-93
WO-A-9117701	28-11-91	NONE	
US-A-4569634	11-02-86	US-A- 4787825	29-11-88
		US-A- 4934902	19-06-90
		US-A- 4740139	26-04-88
EP-A-0321225	21-06-89	US-A- 4852581	01-08-89
		DE-A- 3877170	11-02-93
		US-A- 4974596	04-12-90
US-A-4781535	01-11-88	DE-A- 3871097	17-06-92
		EP-A, B 0320091	14-06-89
		JP-A- 1142284	05-06-89